

PRELIMINARY AMENDMENT  
Attorney Docket No.: Q68109

7. (Amended) A resin-coated metal can obtained by molding a resin-coated metal sheet as claimed in claim 1 in such a manner that the coated layer becomes the inner surface of the can.

AA 8. (Amended) A resin-coated metal closure obtained by molding a resin-coated metal sheet as claimed in claim 1 in such a manner that the coated layer becomes the inner surface of the can closure.

REMARKS

Entry and consideration of this Amendment is respectfully requested.

Respectfully submitted,



Abraham J. Rosner  
Registration No. 33,276

SUGHRUE MION, PLLC  
2100 Pennsylvania Avenue, N.W.  
Washington, D.C. 20037-3213  
Telephone: (202) 293-7060  
Facsimile: (202) 293-7860  
AJR/plr  
Date: January 22, 2002

**APPENDIX**

**VERSION WITH MARKINGS TO SHOW CHANGES MADE**

**IN THE CLAIMS:**

**The claims are amended as follows:**

3. (Amended) A resin-coated metal sheet according to claim 1 [or 2], wherein said resin layer has a melt viscosity of from 2000 to 10,000 centipoises at a temperature of 260°C and at a shearing rate of 122 sec<sup>-1</sup>, and the polyester in the resin layer has an inherent viscosity (IV) in a range of from 0.6 to 1.5.

4. (Amended) A resin-coated metal sheet according to [any one of claims 1 3] claim 1, wherein the ethylene polymer contains an ionomer resin.

7. (Amended) A resin-coated metal can obtained by molding a resin-coated metal sheet [of any one of claims 1 to 6] as claimed in claim 1 in such a manner that the coated layer becomes the inner surface of the can.

8. (Amended) A resin-coated metal closure obtained by molding a resin-coated metal sheet [of any one of claims 1 to 7] as claimed in claim 1 in such a manner that the coated layer becomes the inner surface of the can closure.